

# DYNAplas CELLCRETE 2080 MBS

*Admixture For Cellular and Pre-Foamed Lightweight Concrete*

## DESCRIPTION:

**DYNAplas CELLCRETE 2080 MBS** is a concentrated solution of selected surfactants. When used with a Foam Generator and a suitable water supply, **DYNAplas CELLCRETE 2080 MBS** produces a consistent pre-foam that is stable under alkaline conditions and suitable for use in the production of foamed concrete.

Foamed concrete is the industry term used for the product produced by the controlled addition of a pre-foam to a cement grout or sand/cement mortar. A range of densities can be produced, typically from 350 kg to 1600 kg/M<sup>3</sup>. Foamed concrete is lightweight and highly mobile, able to flow for long distances under its own hydraulic head, and is an ideal material for uses such as void filling, roof screeds and trench reinstatement.

Typical applications for foamed concrete include, but are not limited to:

- Controlled low strength materials
- Trench filling for permanent, non-sink reinstatement
- Elimination of fire risks, health hazards and control of progressive collapse in areas such as underground fuel tanks, below railway platforms, old mine workings, sinkholes, industrial remediation, nuclear decommissioning and abandoned sewers
- As a lightweight thermal insulating material for roof screeds, suspended floors and basements
- As a semi-structural support in embankments, bridge abutments, tunnels and arches

## SPECIFICATIONS:

**DYNAplas CELLCRETE 2080 MBS**  
Conforms to ASTM C 869 "Standard

Specification For Foaming Agents Used In Making Preformed Foam For Cellular Concrete

## ADVANTAGES:

- Produces a consistent, stable pre-foam when used with a Foam Generator
- Easily controlled addition of pre-foam to pre-batched mortar allows close control of finished density
- Expensive blending equipment is not required as mixing can be carried out in the drum of a ready mix truck
- Produces a highly mobile foamed concrete which is easily placed without compaction
- Foamed concrete retains its volume and does not sink during or after hardening

## DOSAGE:

The dosage of **DYNAplas CELLCRETE 2080 MBS** depends upon the original starting materials and the desired final density of the foamed concrete. Typical dosages are in the range of 675 mls to 2500 mls per cubic meter of finished foamed concrete over a density range of 350 kg to 1600 kg/M<sup>3</sup>. The optimum dosage of **DYNAplas CELLCRETE 2080 MBS** to meet specific requirements should always be determined by trials using the materials and conditions that will be experienced in use. Dosages outside the typical range suggested on this data sheet may be used if necessary and suitable to meet particular mix requirements. Contact your local RussTech technical service representative for advice in these cases.

## TECHNICAL NOTE:

**DYNAplas CELLCRETE 2080 MBS** does not contain calcium chloride or any chloride-based components. It will not promote or contribute to corrosion of reinforcing steel in concrete.

### **INSTRUCTIONS FOR USE:**

A pre-foam is produced by feeding **DYNAplas CELLCRETE 2080 MBS** through a Foam Generator. Either a water or air foam generator may be used. No pre-dilution is required with water foam generators. Air foam generators require a pre-dilution ration of 1 part **DYNAplas CELLCRETE 2080 MBS** to 15-35 times water. Foam generators should be fitted with a proportional feeder unit set to correctly dispense **DYNAplas CELLCRETE 2080 MBS**. Only potable water should be used for the pre-foam. Concrete wash water or water from other sources containing high levels of calcium ions should not be used. Refer to the SCL Technical Notes sheets on Foam Generator Operating Procedures and Suitable Mix Designs to generate desired unit weights. Instructions from the SCL Technical Notes should be followed to produce the pre-foam.

### **YIELD:**

Unless extremely tight control is exercised, the density of a foamed concrete is likely to vary by  $\pm 12 \text{ kg/M}^3$ . This variability should be considered when estimating the possible volume of material required. Some factors may affect density and yield. Losses will not always occur but the possibility should be considered. Possible causes of loss include:

- Transportation of foamed concrete over long distances, such as when pre-foam is added at a batch plant instead of onsite
- Delays in placing and pumping
- Foamed concrete placed against a dry substrate causing foam collapse due to the suction of water out of the foamed concrete. If this occurs, wet substrate before placing the foamed concrete to reduce the likelihood of the problem.
- Rain (especially Heavy Rain) falling on unprotected, uncured, placed, foamed concrete.

### **COMPATIBILITY:**

**DYNAplas CELLCRETE 2080 MBS** is compatible with all types of Portland cement, class C and F fly ash, silica fume, calcium chloride, fibers and approved air entraining, accelerating, retarding, Superplasticizing, and water-reducing admixtures. **DYNAplas CELLCRETE 2080 MBS** can be used in white, colored, and architectural concrete. For best results, each admixture must be dispensed separately into the concrete mix.

### **LIMITATIONS:**

Trials should be made using relevant materials and conditions in order to determine the optimum mix design and admixture dosage to meet specific requirements. Compressive strength is proportional to its density and also to the cement content of the original mortar. A number of factors, such as water to cement ratio and the materials used, can affect the unit weight and compressive strength.

**DYNAplas CELLCRETE 2080 MBS** is not intended for direct addition to the mortar and use in this manner will not produce foamed systems. **DYNAplas CELLCRETE 2080 MBS** may not be suitable for use with certain sands, in particular coarse sands. Sands containing a significant amount of particles greater than a #16 sieve should be avoided. Pre-foam should not be made using concrete wash water or water from other sources containing high levels of calcium ions.

**STORAGE:**

**DYN**Aplas **CELL**CRETE **2080 MBS** may freeze at temperatures below 32 F (0 C). Although freezing does not harm **DYN**Aplas **CELL**CRETE **2080 MBS**, precautions should be taken to protect it from freezing. If it should happen to freeze, thaw and reconstitute with mechanical agitation. **Do Not Use Pressurized Air For Agitation.**

**DYN**Aplas **CELL**CRETE **2080 MBS** is an IAI product produced under licence by SCL.

**PACKAGING:**

19 litre pails, 2210 litre drums, and 1000 litre tote tanks.

**SHELF LIFE:**

12 months

**DYN**Aplas **CELL**CRETE **2080 MBS** is manufactured in the USA for SCL (Trinidad) Limited.

SCL also offers the following quality concrete admixtures :-

- Concrete Plasticisers and Superplasticisers
- Concrete retarders
- Concrete accelerators
- Polycarboxylate Superplasticisers
- Rheology modifiers and anti-bleed admixtures
- Anti washout admixtures for underwater applications.
- Corrosion Inhibitors Waterproofing admixtures
- Air entraining agents.
- Admixtures for flowable fill

Revision Date: 07/07/2023

*SCL products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms & Conditions of Sale, copies of which may be obtained on request. Whilst SCL endeavours to ensure that any advice ,recommendations, specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are used, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation or information given by SCL.*